

Technical data sheet

Wetguard 200 SA



- Updated on:** December 16, 2020
- Distributor:** SIGA Cover, Inc.
- Type of application:** Self-adhered membrane for moisture protection of timber elements during the construction phase
- Instructions:** see manual
- Packaging unit:** 61": 16 rolls bound in layers
30": 32 rolls bound in layers
15": 64 rolls bound in layers
- Composition:** Flexible non-woven PO with anti-slip functional layer; full-cover SIGA high-performance modified acrylic-based adhesive. Adhesive side is backed with a polypropylene release film.

Characteristics:

Property		Standards	Units	Values
Dimensions	length / width	61"	feet / inch m / mm	164 / 61.4 50 / 1560
		30"	feet / inch m / mm	164 / 30.7 50 / 780
		15"	feet / inch m / mm	164 / 15.3 50 / 390
Total weight			oz/ft ² g/m ²	0.79 240
Thickness			mils mm	20 0.5
Tensile properties Maximum tensile strength*	MD CD	EN 12311-2	lbs/in	17 14
Tensile properties Elongation*	MD CD	EN 12311-2	%	80 80
Water vapor transmission	Method A (dry cup method)	ASTM E96	US Perms (Ng/Pa.m ² .s)	0.5 28
Outdoor exposure			Weeks	4
Temperature resistance			°F °C	-40°F to +176°F -40°C to +80°C
Application temperature			°F °C	from +14°F from -10°C
Air permeance		ASTM E2178	< 0.004 cfm/ft ²	Pass
Flame spread index		ASTM E84	Index (Rating)	10 (Class A)
Smoke developed index		ASTM E84	Index (Rating)	5 (Class A)